

## EXILVA® BY BORREGAARD

# EXILVA, A SUSTAINABLE CONCRETE VISCOSITY MODIFYING AGENT (VMA)

Choosing the correct mix-design for a concrete is often complex and challenging. The right water to cement (w/c) ratio must be chosen as well as the quantity of other additives, such as superplasticizers (SPs) and viscosity modifying agents (VMAs). A low w/c ratio often gives a concrete with higher strength and durability at the expense of good flow properties.

Superplasticizers, such as poly-carboxylate ethers (PCEs) or lignosulfonates, help with increasing the flowability of the concrete mix-design at a low w/c ratio. However, using SPs can leave the concrete matrix susceptible to bleeding and segregation. To combat this VMAs are used to enhance the resistance to this segregation and bleeding by increasing the yield stress value of the concrete.

A higher yield stress value1 (the energy needed to give complete deformation of a concrete matrix) leads to a more stable and adhesive concrete, reducing the segregation and bleeding. Most VMAs are either oil-based polymers (hydrophobically modified ethylene oxide urethane), inorganic compounds (colloidal silica) or semi-synthetic biopolymers (cellulose ethers, starches and gums). The use of these VMAs also reduces the sustainability of the concrete mix-design. A fine balance of SP and VMA must be used in each concrete mix-design to get the right properties needed.

In this study, we demonstrate how Exilva increases the yield stress of a mortar. Testing was performed by using Exilva P 01-L as a VMA in a cement based mortar, with a SP. Testing a mortar will give a good indication of the type of properties to be expected in the corresponding concrete.

The mortars contained a 3:1 ratio of sand to cement. The SP used was PCE based and was dosed at 1 wt.% (as delivered) liquid by weight of cement (lbwc). The Exilva P 01-L was dosed at 2.5 wt.% (as delivered) lbwc. The w/c ratios tested were 0.4 and 0.45. All mix-designs can be seen in Table 1 below.

| COMPONENT         | Reference (g) | Exilva P 01-L (g) | Reference (g) | Exilva P 01-L (g) |
|-------------------|---------------|-------------------|---------------|-------------------|
| W/C               | 0.4           | 0.4               | 0.45          | 0.45              |
| Sand 0/8          | 667           | 667               | 660           | 660               |
| Std Cement CEM II | 222           | 222               | 220           | 220               |
| Water             | 89            | 83,5              | 100           | 94,5              |
| SP                | 22            | 22                | 20            | 20                |
| Exilva P 01-L     | -             | 5,5               | _             | 5,5               |
| Total (g)         | 1 000         | 1 000             | 1 000         | 1 000             |

#### TABLE 1. Mortar Mix-Design

<sup>1</sup> The rheology of each mortar was measured for yield stress with a rheometer, using the parameters set out in Ouattara, D., et al.2. The results for each mortars' yield stress are shown in Figure 1 (overleaf).







Addition of Exilva P 01-L into a cement mortar increases the yield stress values of the mortar dramatically, even with the presence of the SP. This will produce a corresponding concrete with less segregation and bleeding giving a more cohesive, uniform and workable matrix, as seen in the previous technical bulletin<sup>3</sup>. The increase in the w/c ratio, from 0.4 to 0.45, also shows the robustness of Exilva P 01-L at increasing the yield stress over varying w/c ratios. As generally known, an increase in yield stress will improve adhesion and stability onto the applied surface<sup>2</sup>. This has implications for application with pumping and spraying of concrete by reducing rebound loss, again increasing the sustainability of the concrete.

### **KEY POINTS**

- Addition of Exilva P 01-L, with a PCE based SP, gives an increase in yield stress.
- Increase in Yield Stress reduces the propensity for segregation and bleeding of concretes.
- Robustness of Exilva P 01-L addition of Exilva P 01-L increases yield stress across different w/c ratios.
- Very efficient at low dosages 2.5 wt.% lbwc.
- 100% natural and infinitely sustainable can reduce the CO2 footprint in concrete by replacing oil-based or carbon intensive VMAs<sup>3</sup>.



#### Disclaimer

The information contained in this technical guide on Exilva MFC products and their possible application is for general information purposes only. The information is provided by Borregaard AS and while we endeavour to keep the information up to date and correct, we make no representations or warranties of any kind, express or implied, about the completeness, accuracy, reliability, suitability or availability with respect to the information contained in the Technical Guide for any purpose. Any reliance you place on such information is therefore strictly at your own risk. In no event will we be liable for any loss or damage including without limitation, direct, indirect or consequential loss or damage, or any loss or damage metasting from loss of data or profits arising out of, or in connection with, the use of the information. Construction of the disclaimers above and resolution of disputes thereof are governed by Norwegian law.

<sup>&</sup>lt;sup>1</sup> Ouattara, D., Yahia, A., Mbonimpa, M., & Belem, T., 2017, Effects of superplasticizer on rheological properties of cemented paste backfills. International Journal of Mineral Processing 161, 28-40. <u>https://doi.org/10.1016/j.minpro.2017.02.003</u>

<sup>&</sup>lt;sup>2</sup> Leeman, A., Winnefeld, F., 2007, The effect of viscosity modifying agents on mortar and concrete. Cement & Concrete Composites 29, 341-349. <u>doi:10.1016/j.cemconcomp.2007.01.004</u>

<sup>&</sup>lt;sup>3</sup> Exilva: A Multifunctional Concrete Additive